

Standardizzazione Internazionale della Granulometria per il Diamante e il Nitruro di Boro Cubico (CBN)

Standard "FEPA"		GRANA "Mesh"	Micron range	Nominal
Diamante	CBN			
	301	50/60		50
	251	60/70		60
	213	70/80		70
	181	80/100	150-180	80
	151	100/120	125-150	100
	126	120/140	106-125	120
	107	140/170	90-106	150
	91	170/200	75-90	170
	76	200/230	63-75	220
	64	230/270	53-63	250
	54	270/325	45-53	320
	46	325/400	38-45	400
	45	400/500	36-54	400
	35	500	30-40	500
	30 (29)	600	22-36	600
	25	800	20-30	800
	20	900	15-25	900
	15	1200	8-12	1200
	10	1800	8-16	1800